东莞市万瀚塑胶有限公司
DONGGUAN WANHAN PLASTIC CO., LTD

PCWHRG40A

Properties	Test Standard	Test Unit	Test Value
Mechanical			
Tensile Strength	ISO 527	MPa	65
Elongatlon At Break	ISO 527	%	25
Flexural Strength	ISO178	MPa	95
Tensile Modulus	ISO178	MPa	5450
Izod Notched Impact Strength	ISO180	kJ/m^2	13
Thermal			
Heat deflection temperature	ISO075	℃	130
Melting Flow Index	GB/T3682	g/10min	15
Others			
Density	ISO0895	g/cm^3	1.21
Shrinkage	GB15585	%	0.4-0.6
Flamm ability	UL94	1.6mm	V0

These are typical values of the product 's properties, and these values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes.

NOTICE: The data contained in this publication are based on our current knowledge and experience. This information may be subject to revision without informing in advance as new knowledge and experience become available. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer' s use and for ensuring that Customer' s workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document.

NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE ARE EXPRESSLY EXCLUDED.

Email: gdwanhan@163.com
Website: https://www.wanhan-plastic.com
Whatsapp: +86 13537012277
Address: No. 3 Xingqi East Road, Dongxing District, Dongjiang Science and Technology Park, Zhongkai High-tech Zone, Huizhou City, Guangdong Province, China